



### Application Scheme

	Surface type	Surface preparation	Base	Finish
Exterior	Wooden surface	Waterproofing/felt paper layer + metal lathe coated with layer of powdered Styrofoam mixed with resin mortar <sup>2</sup>	SB <sup>3</sup>	(S1 + Oil + A*) → WA
	Masonry	S	P → M* → SB <sup>3</sup>	or S2 → WA
	ICF	P → (GN + M)	SB <sup>3</sup>	
Interior	Sheetrock	Standard joint treatment. Double layer of sheetrock is recommended.	FC → SB*	(S1 + A*)
	Plywood / OSB	S	(FC + B) → SB*	or (S2 + A*)
	Concrete / concrete block		P → FC → SB*	or S1 → P
	ICF	P → (GN + FC)	SB	
	Wet locations <sup>1</sup>		P → M* → SB	(S1 + Oil + A*) → WA or S2 + A* → WA

FC First Coat

SB Shikkui Base

P UMP - Ultra Maintenance Paste with sand (sand size: <1mm)

M UMM - Ultra Maintenance Mortar

S1 Shikkui Classic, Shikkui Bright, Kodai Shikkui

S2 Shikkui Diatomite

P Polish Paste

Oil Shikkui Oil

\* Optional

WA Waterproofing Agent (apply after finish is completely dry; dry surface is imperative for colored finish)

S Shikkui Sealer

B Shikkui Bond

GN Glass Net

A Antibiotic Agent

A Aggregates

<sup>1</sup> E.g. bathrooms. Only upper part of the wall is recommended for plaster application

<sup>2</sup> Thickness depends on national/local regulations concerning fire protection

<sup>3</sup> Let dry for at least 1 week (for this surface application)